



CRACK FILLER

SURFACE REPAIR & SKIM

- SUPERIOR ADHESION AND DRIES WHITE
- QUICK DRYING AND EASY TO USE
- SLUMP AND SHRINK RESISTANT



DIRECTIONS FOR USE

USAGE PRECAUTIONS

Read all instructions before use. Only use clean tools and mixing containers. Additional water must not be added to product that has started to cure. Only mix enough product to be used within 60 minutes. Never exceed the recommended mixing ratios. Avoid using hot tools and water as this could accelerate curing. Do not dispose unused product in drains. Do not apply to contaminated, under bound or damp surfaces.

APPLICATION INSTRUCTIONS

Crack filler and surface repairs – brick, plaster, concrete, fibre cement, gypsum boards and timber products.

Use a scraper to open up or widen cracks and to remove all loose or flaking material. Wash clean any surface contaminates with Sugar Soap*. Prime metal surfaces with Metal Primer*. Prime under bound surfaces with Bonding liquid*. Add 2 parts Crack Filler to 1 part clean water and mix thoroughly to a smooth uniform paste. Allow to stand for 5 minutes before use. Once mixed Crack Filler remains workable for 60 - 90 minutes. Use a trowel or scraper to apply paste into cracks or holes. Filling cracks deeper than 10mm in one application prolongs drying times. Allow surface to dry for 15 – 20 minutes and smooth off surface with a trowel. Drying time is 2 – 3 hours when applied up to 5mm thick. Sand surface smooth with a medium grit sandpaper. Prime repaired surface with a Plaster Primer* prior to painting.

Skimming Plaster – Suitable for skimming surface imperfections on plaster, concrete, brick, gypsum board, timber and fibre cement surfaces.

Use a scraper to remove all excess loose / flaking material, plaster clumps or high spots. Wash clean any surface contaminates with Sugar Soap*.

Prime metal surfaces with Metal Primer*. Prime under bound surfaces with Bonding liquid*.

Add 2 parts Crack Filler to 1 part water and mix thoroughly to a smooth uniform paste. Allow to stand for 5 minutes before use. Once mixed, Crack Filler remains workable for 60 - 90 minutes. Ensure all tools are clean and undamaged. Apply product to skimming trowel. Set the trowel to the surface at a slight angle of

Manufactured for **PlushLux**

Website: www.plushlux.co.za



approximately 30°. Apply in a thin coat by pulling the trowel in an upward motion towards your body. Spread rate is approximately 2m² / kg when applied at 0.25mm thick.

Skimmed surface can be floated smooth 30 – 45 minutes after application. Any remaining surface imperfections can be sanded smooth with 150 grit sandpaper 2 hours after application. Prime repaired surface with a Plaster Primer* prior to painting.

STORAGE INSTRUCTIONS

Keep product upright and secure container when transporting. Store product in a cool, damp free place out of reach of children. Once product has been opened seal zip lock to prolong shelf life. Do not eat, drink or smoke when using product. Discard product 18 months after batch date (batch number on packaging).

SAFETY INSTRUCTIONS

Read all instructions before use. This product contains cement which is a potential hazard to the eyes, skin and respiratory tracks. Use product in well-ventilated areas. Keep out of reach of children. Store in a secure location. Do not eat, drink or smoke when using product. If medical advice is needed, have product packaging at hand. Use personal protection as required. Wear protective gloves. Wear eye protection. Wear a dust mask. Avoid inhalation of dust.

IF IN EYES Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Seek medical attention if symptoms persist.

IF INHALED Remove victim to fresh air and keep at rest in a position comfortable for breathing. Seek medical attention if symptoms persist.

IF ON SKIN Take off immediately all contaminated clothing and wash before reuse. Wash skin with soapy water. Seek medical attention if symptoms persist.

IF SWALLOWED Do not induce vomiting and seek immediate medical attention. Dispose of contents and packaging in accordance with all local, regional, national and international regulations.

National poison centre 0861 555 777.

